

1
2
3
4
5
6
7
8
9
10
11
12
13
14
15
16
17
18
19
20
21
22

(January 5, 2004)
Coal Tar Pitch Emulsion Seal Coat

Coal Tar Pitch Emulsion

Coal tar pitch emulsion shall meet the requirements of Section 9-02.1(9).

The coal tar pitch emulsion shall be received in its undiluted form and thoroughly mixed to ensure homogeneous consistency of all material.

Aggregates

Aggregate for coal tar pitch seal shall be manufactured silica sand. The aggregate shall meet the following gradation requirements:

US No. 16	100
US No. 30	15-85
US No. 50	5-15
US No. 100	0-2.0
Sand Equivalent	30 min

All percentages are by weight.

Water

Water used shall be potable.